



**Technical Data Sheet
Cast Urethane 65A Food Grade**

Property	Rating or Value
Tensile, PSI	5000
Modulus, 100%	310
Modulus, 300%	500
Hardness, Shore A	65
Elongation, %	725
Bayshore Rebound, %	31
Compression Modulus, psi @ 10%	145

Above values are typical and are only a guide. They are not intended to be used for engineering specifications. End user must test in their application to determine suitability. Values are based on Mbova curative. When cured with Versalink 740M material meets CFR 21-171.1680.